MULTIPPE EP 1





Multi purpose extreme pressure lithium/calcium grease.

APPLICATIONS

Multi purpose EP grease General Lubrication

Recommendation

- MULTIPPE EP 1 is a true multi purpose grease, formulated for lubrication of loaded slide-balland roller-bearings, wheelbearings, universal joints, chassis, and various shock loaded or vibrating applications in transport, agriculture and off road equipment, operating in wet, dusty and/or dry conditions.
- Suitable as general purpose grease for industrial applications requiring a NLGI 1 grade Extreme Pressure grease.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.

SPECIFICATIONS

Meets the requirements of

ISO 6743-9: L-XBCEB 1DIN 51 502: KP1K-30

ADVANTAGES

Durable film
Miscible
Mechanical stability
Thermal stability
No harmful substances

- Because of its true Multi Purpose character MULTIPPE EP 1 may replace a wide range of greases, allowing stock rationalization and simplification of maintenance.
- Forms a durable lubrication film, resulting in reduction of maintenance and down-time costs.
- Miscible with most other conventional soap greases.
- Excellent mechanical stability avoiding ejection or loss of consistency during operation.
- Excellent adhesion to metal.
- Good thermal stability, leading to high resistance to temperature variations.
- MULTIPPE EP 1 does not contain lead, or other heavy metals considered harmful to human health and the environment.

| TYPICAL CHARACTERISTICS | METHODS | UNITS | MULTIPPE EP 1 |
|---------------------------------------------|---------------------------------------|-------------|------------------|
| Soap/thickener | | - | Lithium/ Calcium |
| NLGI grade | ASTM D 217/DIN 51 818 | - | 1 |
| Color | Visual | - | Dark Brown |
| Appearance | Visual | - | Smooth |
| Operating temperature range | | °C | - 30 to 120 |
| Penetration at 25°C | ASTM D 217/DIN51 818 | 0.1 mm | 310 -340 |
| Four ball weld load | DIN 51 350-4 | daN | 260 - 280 |
| Anti-rust performance SKF- EMCOR | DIN 51 802/IP220/NFT 60-135/ISO 11007 | rating | 0 - 0 |
| Dropping point | ASTM D 566/IP 396/NFT 60 102 C | °C | > 190 |
| Kinematic viscosity of the base oil at 40°C | ASTM D 445/DIN 51 562-1/ISO 3104/IP71 | mm²/s (cSt) | 150 |

Above characteristics are mean values given as an information.











